



**Dundy Glass & Mirror Corp** 122-52 Montauk St Springfield Gardens, NY 11413  
718 723 5800 T 718 723 5900 F dundyglass.com

## **LAMINATED SPECIFICATION DATA 6/5/2015**

### **Performance Characteristics of 3/4" Laminated Glass**

Glass Makeup:

3/8" Clear Tempered .060 EVA Translucent White interlayer, 3/8" Clear Tempered

Tensile Strength  $\geq 14$  Mpa

Elongation Break  $\geq 600\%$

Melting Point 65 C

Bonding Strength with Glass  $\geq 10$ KN/M

Water Absorption  $\leq 2\%$

Thermal Shrinkage  $\geq 25\%$

Weight 10 lbs/sq ft

SHGC 0.25

Light Transmittance 9%

UV Protection 99%